

## UPM Raflatac Technical Information

03-04-2020 EN SI

Face	RAFLACOAT PLUS-FSC
Sales Code	FLK
Product	White woodfree machine coated mid-gloss paper.
Use	Designed for quality multicolour labels requiring high contrast and fine printing detail.

### Typical technical values

Substance	80	g/m <sup>2</sup>	ISO 536	
Caliper	70	µm	ISO 534	
Tensile strength MD	5.8	kN/m	ISO 1924/1	
Tensile strength CD	2.8	kN/m	ISO 1924/1	
Brightness	90	%	ISO 2470/1	
Roughness	1.0	µm	ISO 8791	PPS 10
Opacity	88	%	ISO 2471	
Gloss	64	%	Hunter 75°	
CIE Whiteness	120	%	ISO 11475	
Stiffness MD	0.23	mNm	ISO/DP 2493	
Stiffness CD	0.13	mNm	ISO/DP 2493	

**Printability** Suitable for flexography, offset, rotogravure, screen and hot foil. Suitable for thermal transfer printing with wax/resin ribbons. Testing recommended.

**Sustainability** The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCHCOC-004879.

**Disclaimer** The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.